

CEWELD SG CrMoV6

TYPE	Solid wire CrMoV6 for welding similar type of steels. (Air 9117 - 15CDV6)								
APPLICATIONS	CEWELD® SG CrMoV6 is applicable for use in the aerospace and motorsports industries and also in the repair of some tool steels. According AIR 9117, LN 9425 an EN 4334.								
PROPRIÉTÉS	CEWELD® SG CrMoV6 (EN 4334: FE-WL1806 (15CrMnMoV5-4-9-3) wire is used for welding matching, and similar, composition base materials. The weld deposit from Typ 15CrMoV6 provides high strength. Actual mechanical properties will be dependent on specific welding procedure (including shielding gas, PWHT etc) and should always be confirmed by approval of an appropriate welding procedure.								
CLASSIFICATION	DIN	4334 FE-WL1806 (15CrMnMoV5-4-9-3)							
	W.Nr.	1.7734							
CONVIENT POUR	1.7734	15CrMoV6, 25CrMo4, 35CrMo4, 20CrMo12, 15CDV6,							
AGRÉMENTS	CE								
POSITIONS DE SOUDAGE	   								
ANALYSE CHIMIQUE TYPIQUE DU MÉTAL DE SOUDURE (%)	C	Si	Mn	P	S	Cr	Mo	V	Fe
	0.14	0.15	1	0.008	0.008	1.4	0.9	0.22	Rem.
PROPRIÉTÉS MÉCANIQUES	Heat Treatment			R _{P0,2} (MPa)	R _m (MPa)	A5 (%)	Hardness		
	As Welded			850	1100	10	HRc		
ETUVAGE	Not required								
GAS ACC. EN ISO 14175	M21								

CEWELD SG CrMoV6

SG CRM0V6 1,2 MMMM

Packaging	KG/unit	EanCode
BS-300	15	8720682051696