



CEWELD E DUR 63 Nb

TYPE	Basic coated, high Chromium-Niobium based Hardfacing alloy for SMAW			
APPLICATIONS	This electrode with a recovery of 190% can be used for overlays with extremely abrasive and sliding wear resistance, but with low impact. For use till 450 °C.			
PROPRIÉTÉS	Very economical due to the high deposition rate and excellent weldability without slag losses. For critical base material or old hard facing layers it is necessary to buffer with an electrode like CEWELD E DUR 350 Kb / E 11018-G that delivers a welding deposit of less hardness. Overlays on steel with high carbon content should be buffered with CroNi 29/9 HL or 4370 HL. For the best results 2 till 3 layers should be welded.			
CLASSIFICATION	AWS EN ISO DIN F-nr	A 5.13: ~E FeCr-E4 14700: E Fe15 8555: E 10-UM-65- GRZ 71		
CONVIENT POUR	Sugar mill knives and Hammers, Cement mixers, Clinker crushers, Sintering lines, Fire gratings, Mixer blades, Gravel washing equipment, Ceramic mixer blades, Extruders, Crushing tables and Rollers for lime stone etc.			
AGRÉMENTS				
POSITIONS DE SOUDAGE	PAPB			
ANALYSE CHIMIQUE TYPIQUE DU MÉTAL DE SOUDURE (%)	C	Cr	Nb	Fe
	5.75	24	6	Rem.
PROPRIÉTÉS MÉCANIQUES	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A5 (%)
	As Welded			Hardness 60 HRc
ETUVAGE	300°C / 2 hr			
GAS ACC. EN ISO 14175				



CEWELD E DUR 63 Nb

E DUR 63 NB 3,2 X 350MM

Packaging	KG/unit	EanCode
Can	2,5	8720663402653

E DUR 63 NB 4,0 X 450MM

Packaging	KG/unit	EanCode
Can	3	8720663402660