



CEWELD SA Nicro 600 strip



TYPE	Nickel Chromium solid strip									
APPLICATIONS	This strip is suitable for both electroslag (ESW) and sub arc (SAW) process. Typical applications include cladding of vessels for the petrochemical, refinery and chemical industries									
PROPRIÉTÉS	Weld metal deposited by SA Nicro 600 has high strength and good corrosion resistance, including oxidation resistance and creep-rupture strength at elevated temperatures. Use FL 860 ESHC flux									
CLASSIFICATION	AWS	A 5.14: EQNiCr-3								
	EN ISO	18274: B Ni 6082 (NiCr20Mn3Nb)								
	W.Nr.	2.4806								
CONVIENT POUR	SA Nicro 600 is mainly used for ESW and SAW cladding of carbon steel to obtain corrosion and creep resistant layers. Go to FL 860 ESHC suitable flux E Ni 6182 (Ni Cr 15 Fe6Mn), E NiCrFe-3 2.4630, 2.4631, 2.4669, 2.4816, 2.4817, 2.4851, 2.4867, 2.4870, 2.4951 ... (1.4816, 1.4864, 1.4876, 1.4583, 1.4886, 1.5637, 1.5662, 1.5680, 1.6900, 1.6901, 1.6903, 1.6906) NiCr20Ti, NiCr21TiAl, NiCr15Fe7TiAl , NiCr15Fe , LC-NiCr15Fe, NiCr23Fe, NiCr60 15, NiCr80 20, NiCr 10 , NiCr20Ti 1.5637 12 Ni 14, X8Ni9 , 12Ni19 , X12CrNi18 9, GX8CrNi18 10 , X10CrNiTi18 10 , X5CrNi18 10 UNS Nr: K81340 - N06600 - N06601 - N08800 - N08810 ASTM B163, B166, B167 und B168 Alloy 600, Alloy 600 L, Alloy 800 / 800H UNS N06600, N07080, N0800, N0810									
AGRÉMENTS										
POSITIONS DE SOUDAGE										
ANALYSE CHIMIQUE TYPIQUE DU MÉTAL D'APPORT (%)	C	Si	Mn	P	S	Cr	Ni	Nb	Ti	Fe
	0.08	0.4	3	0.02	0.01	21	75	2.8	0.2	2
PROPRIÉTÉS MÉCANIQUES	Heat Treatment			R _{P0,2} (MPa)		R _m (MPa)		A5 (%)		Hardness
	As Welded			390		650		37		HRc
ETUVAGE	Not required									
GAS ACC. EN ISO 14175										