



CEWELD SA Alloy C-276

TYPE	Solid wire for nickel-chromium-molybdenum alloys									
TOEPASSINGEN	CEWELD SA Alloy C-276 is used for welding low carbon nickel-chromium-molybdenum alloys, especially UNS N10276, for welding the clad side in steel clad with low carbon nickel-chromium-molybdenum alloy, and for welding low carbon nickel-chromium-molybdenum alloys to steel and other nickel-base alloys.									
EIGENSCHAPPEN	High Nickel-Chromium alloy with very good mechanical properties down to -196°C. This wire can be welded with our fused flux FL 880 or agglomerated flux FL 838 or FL 839.									
CLASSIFICATIE	AWS	A 5.14: ERNiCrMo-4								
	EN ISO	18274: S Ni 6276 (NiCr15Mo16Fe6W4)								
	W.Nr.	2.4886								
	F-nr	45								
	FM	6								
GESCHIKT VOOR	Alloy 276, Ni 6276 (NiCr15Mo16Fe6W4). 2.4886, 2.4887 M.No: 1.5680, 1.5682, 2.4819, 2.4883 NiMo16Cr15W, X12Ni5 / 12Ni19, X8Ni9, G-NiMo16Cr Alloy C4, Hastelloy C276, A494CW-12MW, A743 / A744CW-12M									
GOEDKEURINGEN										
LASPOSITIES	 									
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	C	Si	Mn	Cr	Ni	Mo	V	Fe	W	Co
	0.01	0.07	0.9	15.5	62	16	0.2	6	4	2
MECHANISCHE WAARDEN	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A5 (%)	Impact Energy (J) ISO-V				Hardness	
					RT					
	As Welded	410	710	35	80				HRc	
HERDROGEN	Not required									
GAS ACC. EN ISO 14175										



CEWELD SA Alloy C-276

SA ALLOY C-276 2,4MM

Packaging	KG/unit	EanCode
K-415	25	8720663420169