


CEWELD 318Si

TYPE	Solid stabilized stainless steel welding wire with high Mo content						
TOEPASSINGEN	Constructions in chemical industries like apparatus and vessels up to working temperatures of approximately 120 °C up to 400 °C.						
EIGENSCHAPPEN	Applicable for welding of joints and surfacings of stabilized, corrosion resistant CrNiMo steels.Excellent corrosion resistance as needed in chemical industry up to 400°C and good weldability with excellent flowing properties due to the increased Silicon content						
CLASSIFICATIE	AWS	A 5.9: ~ER318					
	EN ISO	14343-A: G 19 12 3 Nb Si					
	W.Nr.	1.4576					
	F-nr	6					
	FM	5					
GESCHIKT VOOR	ISO 15608: 8.1 Austenitic ≤ 19 % Cr 1.4301, 1.4306, 1.4401, 1.4404, 1.4408, 1.4420, 1.4435, 1.4436, 1.4541, 1.4550, 1.4571, 1.4573, 1.4579, 1.4580, 1.4581, 1.4583 X 6 CrNiMoTi 17 12 2, X10 CrNiMoTi 18 12, X 6 CrNiMoNb 17 12 2, G-X 5 CrNiMoNb 18 10, X 10 CrNiMoNb 18 12, X 5 CrNiMo 18 11, X 2 CrNiMo 17 13 2, G-X 2 CrNiMo 18 10, X 2 CrNiMo 18 14 3, X 5 CrNiMo 17 12 2, G-X 6 CrNiMo 18 10, X 5 CrNiMo 17 13 3, X6CrNiMoTi17-12-2S UNS S31600, S31603, S31635, S31640, S31653, AISI 316, 316L, 316Ti, 316Cb						
GOEDKEURINGEN	TÜV: (12390), CE, DB: (43.206.03)						
LASPOSITIES	PA PB PC PD PE PF						
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	C	Si	Mn	Cr	Ni	Mo	Nb
	0.07	0.5	2	19	12.5	2.8	0.5
MECHANISCHE WAARDEN	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness
					RT	-60°C	
	As Welded	460	615	35	100	70	HRc
HERDROGEN	Not required						
GAS ACC. EN ISO 14175	M13, M12						



CEWELD 318Si

318Si 0,8MM

Packaging	KG/unit	EanCode
BS-300	15	8720663415103
D-200	5	8720663415110

318Si 1,0MM

Packaging	KG/unit	EanCode
BS-300	15	8720663415127
D-200	5	8720663415141
Drum	250	8720663415134

318Si 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663415158

318Si 1,6MM

Packaging	KG/unit	EanCode
BS-300	15	8720663415165