




CEWELD E DUR 21U

TYPE	Beklede elektrode voor het oplossen van Stellite 21 lagen		
TOEPASSINGEN	Bekleden van klepzittingen, reparatie van bewerkingsgereedschap. Reparatie van schade door erosie, hoge temperatuur en corrosie. Veel toepassingen in de hoge druk stoom-, olie- en petrochemische industrie.		
EIGENSCHAPPEN	Uitstekende weerstand tegen thermische en mechanische schokken. Sterk bij hoge temperaturen.		
CLASSIFICATIE	AWS	A 5.13: E CoCr-E	
	EN ISO	14700: E Co1	
	DIN	8555: E 20-UM-350- CTZ	
	F-nr	71	

GESCHIKT VOOR Stellite 21 alloy for cladding Seats and Valves etc. low friction due to high cobalt content

GOEDKEURINGEN

LASPOSITIES



TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)

C	Si	Mn	Ni	Mo	Fe	Cr	Co
0.3	0.9	1	3	5.5	3	28	Rem.

MECHANISCHE WAARDEN

Heat Treatment	R _{P0.2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
As Welded				35 HRc

HERDROGEN Not required

GAS ACC. EN ISO 14175



CEWELD E DUR 21U

E DUR 21U 2,4 X 350MM

Packaging	KG/unit	EanCode
Can	2,8	8720663402165

E DUR 21U 4,0 X 350MM

Packaging	KG/unit	EanCode
Can	2,8	8720663402189