



CEWELD SA 310

TYPE	High heat resistant stainless steel welding wire for submerged arc welding						
TOEPASSINGEN	Common applications include industrial furnaces, annealing chambers, fused salt treatment installations and boiler parts, as well as heat exchangers..						
EIGENSCHAPPEN	SA 310 is a corrosion-resistant, chromium-nickel wire for welding heat-resistant austenitic steels of the 25% Cr, 20% Ni types. He has good general oxidation resistance, especially at high temperatures, due to its high Cr content. The alloy is fully austenitic and is therefore sensitive to hot cracking. The temperature limits for use under intermittent oxidation depend on cycle frequency. In no case shall a temperature of 1000°C be exceeded. This alloy can withstand relatively severe thermic shock, and is superior to type 309 L. This wire can be welded with our fused flux FL 880 of agglomerated flux FL 838						
CLASSIFICATIE	AWS	A 5.9: ER310					
	EN ISO	14343-A: S 25 20					
	W.Nr.	1.4842					
	F-nr	6					
	FM	5					
GESCHIKT VOOR	ISO 15608: 8.1 Austenitic ≤ 19 % Cr , TÜV 1000: Gr. 21-30, Type: 25% Cr, 22%Ni 1.4710, 1.4713, 1.4724, 1.4726, 1.4742, 1.4745, 1.4762, 1.4823, 1.4826, 1.4828, 1.4832, 1.4835,1.4837, 1.4840, 1.4841, 1.4845, 1.4846, 1.4848, 1.4849, 253MA, X15CrNiSi 25 20, G-X40CrNiSi 25 12, G-X15CrNi 25 20, X8CrNi25-21, GX40CrNiSi22-10, X15CrNiSi20-12, 310, 310S, CK20, 305, 314, 725LN, 316L ASTM A297 HF / A297HJ UNS: S31000, S31008, S31050, S31603						
GOEDKEURINGEN	CE						
LASPOSITIES	 PA  PB  PC						
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	C	Si	Mn	P	S	Cr	Ni
	0.1	0.5	1.8	0.02	0.02	26	21
MECHANISCHE WAARDEN	Heat Treatment	R _{p0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness
					RT	-196°C	
	As Welded	390	590	39	165	55	HRc
HERDROGEN	Not required						
GAS ACC. EN ISO 14175							



CEWELD SA 310

SA 310 2,4MM

Packaging	KG/unit	EanCode
K-415	25	8720663416186